

Technical Laboratory Evaluation

Lab Reporting Form

Comprehensive product information can also be downloaded from www.hrsimon.com



Customer Name: _____
 Address: _____
 Phone: _____
 Facility Name: _____

Date: 10/17/01 8:47
 Samples: _____ From: _____
 Customer Comments: Q/C test-95 F @ 25"

Film:	Agfa	HDR-C	HDR-C
Chemical:		T2AG	UHC
pH:		10.57	10.55
Specific Gravity:		1.0815	1.081

Speed Index:	1.26	1.3
Contrast Index:	1.92	2.01
Base + Fog:	0.27	0.28
Dmax:	4.5	4.55
Average Gradient:	3.20	3.35

Data used to determine Average gradient

St closest to(2+B+F):	2.45	2.56
On Step:	13	13
St closest to(.25+B+F)	0.53	0.55
On Step:	9	9
Step Difference:	4	4

1	0.27	0.28
2	0.29	0.28
3	0.29	0.28
4	0.3	0.29
5	0.31	0.31
6	0.33	0.32
7	0.36	0.35
8	0.41	0.41
9	0.53	0.55
10	0.76	0.79
11	1.26	1.3
12	1.82	1.83
13	2.45	2.56
14	3	3.24
15	3.43	3.6
16	3.82	3.84
17	4.08	4.11
18	4.35	4.39
19	4.5	4.51
20	4.6	4.55
21	4.5	4.55

cc: Mr. Robert Simon
 Mr. Jason Simon

H & D Curves for Comparison

